

Record 3: JP62025106A**(ENG) CONTINUOUS POLYMERIZATION OF OLEFIN****Assignee:** MITSUI PETROCHEMICAL IND

[no drawing available]

Inventor(s): YOSHITAKE JUNICHI ; NAGAMATSU
SHIGEKI ; ODA HIDEKUNI**Application No:** JP 16281985 A**Filing Date:** 19850725**Issue/Publication Date:** 19870203

Abstract: (ENG) <sec>PURPOSE: To produce a polyolefin having improved slurry properties, by polymerizing an olefin in the presence of a catalyst consisting of a highly active Ti component and an organoaluminum compound component in a multistage polymerization process under specific conditions. CONSTITUTION: An olefin is polymerized in the presence of a catalyst consisting of a highly active catalyst component consisting essentially of Mg, Ti and halogen and an organoaluminum compound component in a polymerization apparatus consisting of three or more polymerizers, in which two or more polymerizers are connected in series in a multistage continuous polymerization process. In the process, a catalyst prepared by prepolymerizing a 3W6C α -olefin in a hydrocarbon medium is used to polymerize 0.1W5wt%, based on the total olefin, olefin in one or more steps in the process and to give an ultrahigh- molecular weight polyolefin having ≥ 15 dl/g intrinsic viscosity $[\eta]$. The residual olefin is polymerized in the other steps in the presence of hydrogen to afford the polyolefin having respectively different intrinsic viscosities $[\eta]$ lower than the $[\eta]$.</sec>

Priority Data: JP 16281985 19850725 A X;